

GRAPHISTRENGTH[®] C S-350

CARBON NANOTUBE STRENGTHENED LIQUID EPOXY RESIN

TECHNICAL DATA SHEET

Description:

Graphistrength[®] C S-350 is a bisphenol-A multi-wall carbon nanotube strengthened liquid epoxy resin suitable for numerous composites and adhesives applications.

Key features:

Graphistrength[®] C S-350 has the following key characteristics:

Property	Method	Unit	Typical value ⁽¹⁾
Aspect	Visual		Black
EEW	ISO 3000	g/eq	194-202
Viscosity at 25°C	Rheometer	mPa.s	8,000-9,500
Density at 25°C	ISO 1675	g/cm ³	1.16

⁽¹⁾ Data not intended for specification purposes

Applications and benefits:

Graphistrength[®] C S-350 is recommended for use in composite manufacturing processes such as filament winding, pultrusion, and wet lay-up. Graphistrength[®] C S-350 can be used with most reinforcing fibers and fabrics, such as carbon, glass, and aramid. It can also be used in adhesives and coatings applications.

The carbon nanotube enhancement makes Graphistrength[®] C S-350 a high strength epoxy resin. It also processes as easily as unfilled epoxy resin and can be cured with a wide range of curing agents.

The use of Graphistrength[®] C S-350 allows a considerable increase in flexural and compression properties of composites.

Graphistrength[®] C S-350 has the lowest viscosity in the bisphenol-A based Graphistrength[®] line.

Dilution and processing:

Strengthened with an optimum level of carbon nanotubes, Graphistrength[®] C S-350 can be used in the same conditions as for classical epoxy liquid resins.

Graphistrength[®] C S-350 can be used with different kinds of hardeners depending on the desired mechanical properties. As for classical bisphenol-A resins, mixing the resin with the hardener can be easier with preliminary heating of Graphistrength[®] C S-350 at 70 °C or more.

Typical properties:

Mechanical properties of the cured Graphistrength[®] C S-350 resin

System	
Curing agent (anhydride)	Lindride LS81K
Resin	Graphistrength [®] C S-350
Resin/Curing (phr)	100/100
Mix viscosity at 25°C (mPa.s)	1,300 – 1,500
Pot life, 2x Initial viscosity (h)	8
Gel time at 150°C (s)	68
Cure Cycle	1,5h at 65°C, 1h at 85°C; 3h at 150°C
Properties⁽²⁾	
Flexural Strength (MPa)	180
Flexural Modulus (MPa)	3,500
Compression Strength (MPa)	115
Compression Modulus (MPa)	4,150
Tg (°C)	140

⁽²⁾ Data are intended solely for indicating potential performance that can be achieved. They don't replace the reader's own evaluations and experimentation

Mechanical properties of a composite powered by Graphistrength[®] C S-350 resin

Wet lay-up/autoclave (0,5MPa)

Composite	
Curing agent (anhydride)	LS81K
Carbon fabric ratio	60%vol
Carbon Fabric type	Plain weave
Number of fabric plies	4
Cure cycle	3h at 150°C
Properties⁽³⁾	
Flexural Strength (MPa)	607 (+45%)
Flexural Modulus (MPa)	45,000 (+30%)
Compression Strength (MPa)	187 (+32%)
Compression Modulus (MPa)	25,000 (+40%)

⁽³⁾ Data are intended solely for indicating potential performance that can be achieved. They don't replace the reader's own evaluations and experimentation

Packaging and Storage:

Graphistrength[®] C S-350 is provided in drums of 20kg or 220kg net.
Graphistrength[®] C S-350 should be stored in dry place, preferably in its sealed original container, at temperatures between 2 and 40°C. In these storage conditions, the shelf life is more than 9 months.
The product should not be stored exposed to direct sunlight. A potential crystallization of the product could occur. It can be restored to its original state by stirring at 70 °C.

Safety and Handling:

Graphistrength[®] C S-350 doesn't present any specific health risk when using in thermoset processing. Mandatory and recommended industrial hygiene procedures should be followed whenever the product is being handled and processed.
Consult the product MSDS for additional information on properties, hazards and handling.

Contacts:

- www.graphistrength.com
- **Europe**
Arkema France –
+33 (0)4 72 39 58 14
- **Japan**
Arkema K.K. –
+81 (0)75 326 75 15
- **North America**
Arkema Inc. –
+1 610 878 69 92

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, expressed or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing, or use of the product or products concerned - which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.

The statements, technical information, and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials, or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See MSDS for Health & Safety Considerations.

Arkema France
420, rue d'Estienne d'Orves
92705 COLOMBES Cedex – France
Tel.: + 33 1 49 00 80 80 - Fax: 33 1 49 00 83 96
www.arkema.com

Graphistrength[®] C S-350 is developed in collaboration with Zyvex Performance Materials

www.zyvexpro.com

zyvex[™]
performance
materials